

## The Features of Rhenium Deformation Behavior at Room Temperature

Peter Panfilov

Institute of Natural Sciences and Mathematics, Ural Federal University, Lenin ave. 51, 620083, Ekaterinburg,  
Russia

Received: June 09, 2020

Corresponding author: Peter Panfilov

**Abstract.** Being the refractory hexagonal close-packed metal, rhenium is characterized by the ductile deformation behavior in the single crystalline state, but sometimes it behaves like a brittle solid in the polycrystalline form. The plasticity of the polycrystalline rhenium depends on the share of the tensile stress in the loading scheme and varies from low under bending to considerable under shearing. The grain boundary sliding is the factor that limited the malleability of rhenium work-pieces; it occurs because the basal slip is the primary deformation mechanism in rhenium at room temperature, as it takes place in zinc and ruthenium.

### ACKNOWLEDGMENT

The Russian Science Foundation supports this work (#18-19-00217).

### REFERENCES

- [1] R.W.K. Honeycombe, *The plastic deformation of metals* (London, Edward Arnold, 1968).
- [2] A.S. Argon, *Strengthening Mechanisms in Crystal Plasticity* (Oxford, Oxford University Press, 2007).
- [3] J. Friedel, *Dislocations* (Oxford, Pergamon Press, 1964).
- [4] J.P. Hirth and J. Lothe, *Theory of Dislocations* (New York, McGraw-Hill, 1968).
- [5] R.A. Jeffrey and E. Smith, *Deformation twinning in rhenium single crystals*, Phil. Mag., 1966, vol.13, no. 126, pp. 1163 – 1168.
- [6] C.T. Sims, C.M. Craighead and R.I. Jaffee, *Physical and mechanical properties of rhenium*, JOM, 1955, vol. 1, no. 1, pp. 168 – 179.
- [7] V. Kopetskii, M.M. Myshlyaev, N.I. Novochatskaia and Yukhanov, *Study of plastic deformation of rhenium single crystals*, Physics of Metals and Metallography, 1975, vol. 39, no. 1, pp. 164-174 (in Russian).
- [8] J.E.C. Sabisch and A.M. Minor, *Microstructural evolution of rhenium Part I: Compression*, Materials Science & Engineering A, 2018, vol. 732, pp. 251 – 258.

- [9] J.E.C. Sabisch and A.M. Minor, *Microstructural evolution of rhenium Part II: Tension*, Materials Science & Engineering A, 2018, vol. 732, pp. 259 – 272.
- [10] I.L. Shabalina, *Rhenium*, In: Ultra-High Temperature Materials I (London, Springer, 2014), pp. 317 – 358.
- [11] J.R. Handley, *Increasing application for iridium*, Platinum Metals Rev., 1986, vol. 30, Nn 1, pp. 12 – 13. <https://www.technology.matthey.com/article/30/1/12-13/>
- [12] J-C. Carlen and B.D. Bryskin, *Rhenium – a unique rare metal*, Materials and Manufacturing Processes, 1994. vol. 9, no. 6, pp. 1087 – 1104.
- [13] E. K. Ohriner, *Rhenium and iridium*, MCD ORLN, preprint No Conf-970201-6, 1996, 17 p.
- [14] E. K. Ohriner, *Processing of Iridium and Iridium Alloys. Methods from purification to fabrication*, Platinum Metals Rev., 2008, vol. 52, no. 3, pp. 186-197.
- [15] P. Panfilov, A. Yermakov, V. Dmitriev and N. Timofeev, *Plastic flow of iridium*, Platinum Metals Rev, 1991, vol. 35, no. 4, pp. 196-200.
- [16] R.I. Jaffee, D.J. Maykuth and R.W. Douglass, *Rhenium and refractory Platinum-Group Metals*, In: *Refractory Metals and Alloys*, AIME Metallurgical Society Conferences, vol. 11, ed. by M. Semchyshen and J.J. Harwood (New York, Interscience, 1961), pp. 383-463.,
- [17] I.S. Servi, *Tensile ductility of rhenium at 1200 °C*, J. Less-Common Metals, 1969, vol. 17, pp. 340 - 343.
- [18] J. Kacher and A.M. Minor, *Twin boundary interactions with grain boundaries investigated in pure rhenium*, Acta Materialia, 2014, vol. 81, pp. 1–8.
- [19] P. Panfilov, Yu.N. Gornostyrev, D. Zaytsev, G.P. Panfilov and V.P. Pilyugin, *On deformation behavior of polycrystalline rhenium under three-points bending at room temperature*, IOP Conf. Series: Materials Science and Engineering, 2019, vol. 581, art. 012028 (IOP Publishing doi: [10.1088/1757-899X/581/1/012](https://doi.org/10.1088/1757-899X/581/1/012)).
- [20] P. Panfilov, G.P. Panfilov and D. Zaytsev, *Deformation behavior of polycrystalline rhenium under shear testing at room temperature*, Materials Letters, 2020, vol. 277, art. 128379.
- [21] P. Panfilov, T.P. Tolmachev, V.P. Pilyugin, Z. Chen and Z.L. Zhang, *The forming of the ultra-fine grain structure in coarse grain rhenium under high-pressure torsion at room temperature*, Materials Letters, 2020, in press.
- [22] P. Panfilov and A. Yermakov, *Plastic deformation and fracture of ruthenium single crystals*, Platinum Metals Rev., 1994, vol. 38, no. 1, pp. 12-15.