

## Electrical and Mechanical Properties of Zirconia-Graphene Composites

A.G. Glukharev<sup>1,2</sup>, V.G. Konakov<sup>1,2</sup> and O.Yu. Kurapova<sup>2,3</sup>

<sup>1</sup>Institute for Problems in Mechanical Engineering, V.O., Bolshoj pr. 61, St. Petersburg, 199178, Russia

<sup>2</sup>Peter the Great St. Petersburg Polytechnic University, Politehnicheskaya, St. Petersburg, 195251, Russia

<sup>3</sup>Institute of chemistry, St. Petersburg State University, Universitetskaya emb. 7-9, St. Petersburg, 199034, Russia

Received: December 15, 2020

Corresponding author: A.G. Glukharev

**Abstract.** The paper reviews the available data on the electrical and mechanical properties of zirconia-graphene composites. The effects of the graphene additive type, synthesis approach, and graphene additive contents are analyzed in terms of these composites application in solid oxide fuel cells.

## REFERENCES

- [1] A. K. Geim and K. S. Novoselov, *The rise of graphene*, Nat. Mater., 2007, vol. 6, no. 3, pp. 183–191.
- [2] H. Shioyama, *Cleavage of graphite to graphene*, J. Mater. Sci. Lett., 2001, vol. 20, no. 6, pp. 499–500.
- [3] P. Shemella and S. K. Nayak, *Electronic structure and band-gap modulation of graphene via substrate surface chemistry*, Appl. Phys. Lett., 2009, vol. 94, no. 3, art. 032101.
- [4] D. Yuan and F.A. Kroeger, *Stabilized Zirconia as an Oxygen Pump*, Electrochem Soc-J, 1969, vol. 116, no. 5, pp. 594–600.
- [5] V. S. Stubican, R. C. Hink and S. P. Ray, *Phase Equilibria and Ordering in the System  $ZrO_2$ - $Y_2O_3$* , J. Am. Ceram. Soc., 1978, vol. 61, no. 1–2, pp. 17–21.
- [6] H. Yanagida, K. Komoto and M. Miyayama, *The chemistry of ceramics* (Wiley, 1996).
- [7] A. Ghazanfari, W. Li, M. C. Leu, J. L. Watts and G. E. Hilmas, *Additive manufacturing and mechanical characterization of high density fully stabilized zirconia*, Ceramics International, 2017, vol. 43, no. 8, pp. 6082–6088.
- [8] J. Zhang, *Thermal cycling effect on mechanical properties of Yttria-stabilized tetragonal zirconia*, Key Engineering Materials, 2013, vol. 538, pp. 121–124.
- [9] T. Masaki, *Mechanical properties of toughened  $ZrO_2$ - $Y_2O_3$  Ceramics*, J. Am. Ceram. Soc., 1986, vol. 69, no. 8, pp. 638–640.
- [10] T. Sato and M. Shimada, *Transformation of Yttria-Doped Tetragonal  $ZrO_2$  Polycrystals by Annealing in Water*, J. Am. Ceram. Soc., 1985, vol. 68, no. 6, pp. 356–356.
- [11] N. Mahato, A. Banerjee, A. Gupta, S. Omar and K. Balani, *Progress in material selection for solid oxide fuel cell technology: A review*, Prog. Mater. Sci., 2015, vol. 72, pp. 141–337.
- [12] J. M. Dixon, L. D. LaGrange, U. Merten, C. F. Miller and J. T. Porter, *Electrical Resistivity of Stabilized Zirconia at Elevated Temperatures*, J. Electrochem. Soc., 1963, vol. 110, no. 4, pp. 276–279.
- [13] D. W. Strickler and W. G. Carlson, *Ionic Conductivity of Cubic Solid Solutions in the System  $CaO$ — $Y_2O_3$ — $ZrO_2$* , J. Am. Ceram. Soc., 1964, vol. 47, no. 3, pp. 122–127.
- [14] R. E. W. Casselton, *Low field DC conduction in yttria-stabilized zirconia*, Phys. Status Solidi, 1970, vol. 2, no. 3, pp. 571–585.
- [15] J. A. Kilner and C. D. Waters, *The effects of dopant cation-oxygen vacancy complexes on the anion transport properties of non-stoichiometric fluorite oxides*, Solid State Ionics, 1982, vol. 6, no. 3, pp. 253–259.
- [16] J.A. Kilner and B.C.H. Steele, *Mass Transport in Anion-Deficient Fluorite Oxides*, In: Nonstoichiometric Oxides, ed. by O. Toft Sørensen (Academic Press, N.Y., 1981), pp. 233–269.

- [17] H. L. Tuller, Ionic conduction in nanocrystalline materials, *Solid State Ionics*, 2000, vol. 131, no. 1, pp. 143–157.
- [18] P. Mondal, A. Klein, W. Jaegermann and H. Hahn, *Enhanced specific grain boundary conductivity in nanocrystalline  $Y_2O_3$ -stabilized zirconia*, *Solid State Ionics*, 1999, vol. 118, no. 3–4, pp. 331–339.
- [19] X. Guo and R. Waser, *Electrical properties of the grain boundaries of oxygen ion conductors: Acceptor-doped zirconia and ceria*, *Progress in Materials Science*, 2006, vol. 51, no. 2, pp. 151–210.
- [20] V. Singh, S. Babu, A. S. Karakoti, A. Agarwal and S. Seal, *Effect of Submicron Grains on Ionic Conductivity of Nanocrystalline Doped Ceria*, *J. Nanosci. Nanotechnol.*, 2010, vol. 10, pp. 1–9.
- [21] S. P. S. Badwal, *Grain boundary resistivity in zirconia-based materials: effect of sintering temperatures and impurities*, *Solid State Ionics*, 1995, vol. 76, no. 1–2, pp. 67–80.
- [22] J. M. Ralph, J. A. Kilner and B. C. H. Steele, *Improving gd-doped ceria electrolytes for low temperature solid oxide fuel cells*, *Mater. Res. Soc. Symp. - Proc.*, 1999, vol. 575, pp. 309–314.
- [23] X. Guo, *Effect of  $Nb_2O_5$  on the space-charge conduction of  $Y_2O_3$ -stabilized  $ZrO_2$* , *Solid State Ionics*, 1997, vol. 99, no. 1–2, pp. 137–142.
- [24] X. Guo, *Space-charge conduction in yttria and alumina codoped-zirconia*, *Solid State Ionics*, 1997, vol. 96, no. 3–4, pp. 247–254.
- [25] J.-H. Lee, T. Mori, J.-G. Li, T. Ikegami, M. Komatsu and H. Haneda, *Improvement of Grain-Boundary Conductivity of 8 mol % Yttria-Stabilized Zirconia by Precursor Scavenging of Siliceous Phase*, *J. Electrochem. Soc.*, 2000, vol. 147, no. 7, pp. 2822–2829.
- [26] Hannes C. Schniepp, Je-Luen Li, Michael J. McAllister, Hiroaki Sai, Margarita Herrera-Alonso, Douglas H. Adamson, Robert K. Prud'homme, Roberto Car, Dudley A. Saville, and Ilhan A. Aksayhttps://doi.org/10.1021/j30605359, *Functionalized single graphene sheets derived from splitting graphite oxide*, *J. Phys. Chem. B*, 2006, vol. 110, no. 17, pp. 8535–8539.
- [27] S. Pei and H. M. Cheng, *The reduction of graphene oxide*, *Carbon*, 2012, vol. 50, no. 9, pp. 3210–3228.
- [28] J. Chen, B. Yao, C. Li and G. Shi, *An improved Hummers method for eco-friendly synthesis of graphene oxide*, *Carbon*, 2013, vol. 64, pp. 225–229.
- [29] Sasha Stankovich, Dmitriy A. Dikin, Richard D. Piner, Kevin A. Kohlhaas, Alfred Kleinhammes, Yuanyuan Jia, Yue Wu, Son Binh T. Nguyen and Rodney S. Ruoff, *Synthesis of graphene-based nanosheets via chemical reduction of exfoliated graphite oxide*, *Carbon*, 2007, vol. 45, no. 7, pp. 1558–1565.
- [30] Dongxing Yang, Aruna Velamakanni, Gülay Bozoklu, Sungjin Park, Meryl Stoller, Richard D. Piner, Sasha Stankovich, Inhwa Jung, Daniel A. Field, Carl A. Ventrice Jr. and Rodney S. Ruoff, *Chemical analysis of graphene oxide films after heat and chemical treatments by X-ray photoelectron and Micro-Raman spectroscopy*, *Carbon*, 2009, vol. 47, no. 1, pp. 145–152.
- [31] M. J. Fernández-Merino, L. Guardia, J. I. Paredes, S. Villar-Rodil, P. Solís-Fernández, A. Martínez-Alonso and J. M. D. Tascón, *Vitamin C is an ideal substitute for hydrazine in the reduction of graphene oxide suspensions*, *J. Phys. Chem. C*, 2010, vol. 114, no. 14, pp. 6426–6432.
- [32] Hyeyon-Jin Shin, Ki Kang Kim, Anass Benayad, Seon-Mi Yoon, Hyeyon Ki Park, In-Sun Jung, Mei Hua Jin, Hae-Kyung Jeong, Jong Min Kim, Jae-Young Choi and Young Hee Lee, *Efficient Reduction of Graphite Oxide by Sodium Borohydride and Its Effect on Electrical Conductance*, *Adv. Funct. Mater.*, 2009, vol. 19, no. 12, pp. 1987–1992.
- [33] R. S. Dey, S. Hajra, R. K. Sahu, C. R. Raj and M. K. Panigrahi, *A rapid room temperature chemical route for the synthesis of graphene: Metal-mediated reduction of graphene oxide*, *Chem. Commun.*, 2012, vol. 48, no. 12, pp. 1787–1789.
- [34] W. Gao, L. B. Alemany, L. Ci and P. M. Ajayan, *New insights into the structure and reduction of graphite oxide*, *Nat. Chem.*, 2009, vol. 1, no. 5, pp. 403–408.
- [35] J. N. Ding, Y. B. Liu, N. Y. Yuan, G. Q. Ding, Y. Fan and C. T. Yu, *The influence of temperature, time and concentration on the dispersion of reduced graphene oxide prepared by hydrothermal reduction*, *Diam. Relat. Mater.*, 2012, vol. 21, pp. 11–15.
- [36] H. A. Becerril, J. Mao, Z. Liu, R. M. Stoltberg, Z. Bao and Y. Chen, *Evaluation of solution-processed reduced graphene oxide films as transparent conductors*, *ACS Nano*, 2008, vol. 2, no. 3, pp. 463–470.
- [37] X. Wang, L. Zhi and K. Müllen, *Transparent, conductive graphene electrodes for dye-sensitized solar cells*, *Nano Lett.*, 2008, vol. 8, no. 1, pp. 323–327.
- [38] X. Xie, Y. Zhou and K. Huang, *Advances in Microwave-Assisted Production of Reduced Graphene Oxide*, *Front. Chem.*, 2019, vol. 7, art. 00355.
- [39] P. Miranzo, M. Belmonte and M. I. Osendi, *From bulk to cellular structures: A review on ceramic/graphene filler composites*, *J. Eur. Ceram. Soc.*, 2017, vol. 37, no. 12, pp. 3649–3672.
- [40] A. Nieto, A. Bisht, D. Lahiri, C. Zhang and A. Agarwal, *Graphene reinforced metal and ceramic matrix*

- composites: a review*, International Materials Reviews, 2017, vol. 62, no. 5, pp. 241–302.
- [41] L. S. Walker, V. R. Marotto, M. A. Rafiee, N. Koratkar and E. L. Corral, *Toughening in graphene ceramic composites*, ACS Nano, 2011, vol. 5, no. 4, pp. 3182–3190.
- [42] H. Porwal, P. Tatarko, S. Grasso, J. Khalil, I. Dlouhý and M. J. Reece, *Graphene reinforced alumina nano-composites*, Carbon, 2013, vol. 64, pp. 359–369.
- [43] C. Ramirez, L. Garzón, P. Miranzo, M. I. Osendi and C. Ocal, *Electrical conductivity maps in graphene nanoplatelet/silicon nitride composites using conducting scanning force microscopy*, Carbon, 2011, vol. 49, no. 12, pp. 3873–3880.
- [44] Jian Liu, Yang Yang, Hany Hassain, Neeraj Jumbu, Sunan Deng, Qian Zuo and Kyle Jiang, *Graphene-Alumina Nanocomposites with Improved Mechanical Properties for Biomedical Applications*, ACS Appl. Mater. Interfaces, vol. 8, no. 4, pp. 2607–2616.
- [45] Harshit Porwal, Peter Tatarko, Salvatore Grasso, Chunfeng Hu, Aldo R. Boccaccini, Ivo Dlouhý and Mike J. Reece, *Toughened and machinable glass matrix composites reinforced with graphene and graphene-oxide nano platelets*, Sci. Technol. Adv. Mater., 2013, vol. 14, no. 5.
- [46] Yuchi Fan, Lianjun Wang, Jianlin Li, Jiaqi Li, Shikuan Sun, Feng Chen, Lidong Chen and Wan Jiang, *Preparation and electrical properties of graphene nanosheet/Al<sub>2</sub>O<sub>3</sub> composites*, Carbon, vol. 48, no. 6, pp. 1743–1749.
- [47] P. Kun, O. Tapasztó, F. Wéber and C. Balázs, *Determination of structural and mechanical properties of multilayer graphene added silicon nitride-based composites*, Ceram. Int., 2012, vol. 38, no. 1, pp. 211–216.
- [48] J. I. Paredes, S. Villar-Rodil, A. Martínez-Alonso and J. M. D. Tascón, *Graphene oxide dispersions in organic solvents*, Langmuir, vol. 24, no. 19, pp. 10560–10564.
- [49] Y. Hernandez *et al.*, *High-yield production of graphene by liquid-phase exfoliation of graphite*, Nat. Nanotechnol., 2008, vol. 3, no. 9, pp. 563–568.
- [50] B. Lee, M. Y. Koo, S. H. Jin, K. T. Kim and S. H. Hong, *Simultaneous strengthening and toughening of reduced graphene oxide/alumina composites fabricated by molecular-level mixing process*, Carbon, 2014, vol. 78, pp. 212–219.
- [51] X. Yu, J. Xu, H. Lu and G. Fang, *Sol-gel derived Al-doped zinc oxide – Reduced graphene oxide nanocomposite thin films*, J. Alloys Compd., 2017, vol. 699, pp. 79–86.
- [52] Cristina Ramírez, Sofia M. Vega-Díaz, Aaron Morelos-Gómez, Filipe M. Figueiredo, Mauricio Terrones, María Isabel Osendi, Manuel Belmonte and Pilar Miranzo, *Synthesis of conducting graphene/Si<sub>3</sub>N<sub>4</sub> composites by spark plasma sintering*, Carbon, 2013, vol. 57, pp. 425–432.
- [53] T. Ukai, Tohru Sekino, Ari T. Hirvonen, Norihito Tanaka, Takafumi Kusunose, Tadachika Nakayama and Koichi Niijima, *Preparation and Electrical Properties of Carbon Nanotubes Dispersed Zirconia Nanocomposites*, Key Eng. Mater., 2006, vol. 317–318, pp. 661–664.
- [54] K. Markandan, J. K. Chin and M. T. T. Tan, *Enhancing electroconductivity of yttria-stabilised zirconia ceramic using graphene platelets*, Key Eng. Mater., 2016, vol. 690, pp. 1–5.
- [55] Y. Fan, L. Kang, W. Zhou, W. Jiang, L. Wang and A. Kawasaki, *Control of doping by matrix in few-layer graphene/metal oxide composites with highly enhanced electrical conductivity*, Carbon, 2015, vol. 81, no. 1, pp. 83–90.
- [56] B. Román-Manso, E. Domingues, F. M. Figueiredo, M. Belmonte and P. Miranzo, *Enhanced electrical conductivity of silicon carbide ceramics by addition of graphene nanoplatelets*, J. Eur. Ceram. Soc., 2015, vol. 35, no. 10, pp. 2723–2731.
- [57] R. Poyato, J. Osuna, A. Morales-Rodríguez and Gallardo-López, *Electrical conduction mechanisms in graphene nanoplatelet/yttria tetragonal zirconia composites*, Ceram. Int., 2018, vol. 44, no. 12, pp. 14610–14616.
- [58] D. Marinha and M. Belmonte, *Mixed-ionic and electronic conduction and stability of YSZ-graphene composites*, J. Eur. Ceram. Soc., 2019, vol. 39, no. 2–3, pp. 389–395.
- [59] Y. Fan, W. Jiang and A. Kawasaki, *Highly Conductive Few-Layer Graphene/Al<sub>2</sub>O<sub>3</sub> Nanocomposites with Tunable Charge Carrier Type*, Adv. Funct. Mater., 2012, vol. 22, no. 18, pp. 3882–3889.
- [60] M. Drozdova, D. Pérez-Coll, M. Aghayan, R. Ivanov, M. A. Rodríguez and I. Hussainova, *Hybrid graphene/alumina nanofibers for electroconductive zirconia*, Key Eng. Mater., 2016, vol. 674, pp. 15–20.
- [61] C. Ramirez, M.I. Osendi, P. Miranzo, M. Belmonte, F. Figueiredo, A. Castro-Beltrán and M. Terrones, *Graphene nanoribbon ceramic composites*, Carbon, 2015, vol. 90, pp. 207–214.
- [62] Y. Teraoka, H. M. Zhang, K. Okamoto and N. Yamazoe, *Mixed ionic-electronic conductivity of La<sub>1-x</sub>Sr<sub>x</sub>Co<sub>1-y</sub>FeyO<sub>3-δ</sub> perovskite-type oxides*, Mater. Res. Bull., 1988, vol. 23, no. 1, pp. 51–58.
- [63] J. Sunarso, S. Baumann, J.M. Serra, W.A. Meulenberg, S. Liu, Y.S. Lin and J.C. Diniz da Costa, *Mixed ionic-electronic conducting (MIEC) ceramic-based membranes for oxygen separation*, Journal of Membrane

Science, 2008, vol. 320, no. 1–2, pp. 13–41.

- [64] Philippe Vernoux, Leonardo Lizarraga, Mihalis N. Tsampas, Foteini M. Sapountzi, Antonio De Lucas-Consuegra, Jose-Luis Valverde, Stamatios Souentie, Costas G. Vayenas, Dimitris Tsiplakides, Stella Balomenou and Elena A. Baranova, *Ionically conducting ceramics as active catalyst supports*, Chemical Reviews, 2013, vol. 113, no. 10, pp. 8192–8260.
- [65] Y. Fan, L. Kang, W. Zhou, W. Jiang, L. Wang and A. Kawasaki, *Control of doping by matrix in few-layer graphene/ metal oxide composites with highly enhanced electrical conductivity*, Carbon, 2015, vol. 81, no. 1, pp. 83–90.
- [66] J. P. Moore, R. S. Graves and D. L. McElroy, *Thermal and Electrical Conductivities and Seebeck Coefficients of Unirradiated and Irradiated Graphites from 300 To 1000 K*, Oak Ridge National Laboratory, Jan. 1973
- [67] J. H. Shin and S. H. Hong, *Fabrication and properties of reduced graphene oxide reinforced yttria-stabilized zirconia composite ceramics*, J. Eur. Ceram. Soc., 2014, vol. 34, no. 5, pp. 1297–1302.
- [68] Fei Chen, Dongqin Jin, Khalid Tyeb, Botao Wang, Young-Hwan Han, Sukyoung Kim, Julie M. Schoenung, Qiang Shen and Lianmeng Zhang, *Field assisted sintering of graphene reinforced zirconia ceramics*, Ceram. Int., 2015, vol. 41, no. 4, pp. 6113–6116.
- [69] X. Wang, N. P. Padture and H. Tanaka, *Contact-damage-resistant ceramic/single-wall carbon nanotubes and ceramic/graphite composites*, Nat. Mater., 2004, vol. 3, no. 8, pp. 539–544.
- [70] J. Su, Y. Chen and Q. Huang, *Graphene nanosheet-induced toughening of yttria-stabilized zirconia*, Appl. Phys. A Mater. Sci. Process., 2017, vol. 123, no. 1, pp. 1–11.
- [71] R. Cano-Crespo, B. M. Moshtaghioun, D. Gómez-García, R. Moreno and A. Domínguez-Rodríguez, *Graphene or carbon nanofiber-reinforced zirconia composites: Are they really worthwhile for structural applications?*, J. Eur. Ceram. Soc., 2018, vol. 38, no. 11, pp. 3994–4002.
- [72] S. Ramesh *et al.*, *Sintering behaviour and properties of graphene oxide-doped Y-TZP ceramics*, Ceram. Int., 2016, vol. 42, no. 15, pp. 17620–17625.
- [73] O. Y. Kurapova, A. G. Glukharev, O. V. Glumov, M. Y. Kurapov, E. V. Boltynjuk and V. G. Konakov, *Structure and electrical properties of YSZ-rGO composites and YSZ ceramics, obtained from composite powder*, Electrochim. Acta, 2019, vol. 320, art. 134573, 2019.

(c) 2020 ITMO